

## ENGINEERING DATASHEET

**EVEREADY BATTERY CO.** Internet: www.energizer.com


1-800-383-7323 / USA 1-800-383-7323 / CANADA

+ 44 (0) 208 920 2306 / EUROPE


# **ENERGIZER NO. NH22**




#### **Industry Standard Dimensions in mm (inches)**



### TYPICAL DISCHARGE CHARACTERISTICS Average Performance at 21°C (70°F)



### TYPICAL DISCHARGE CHARACTERISTICS Average Performance at 21°C (70°F)



# 9V

**Description:** Rechargeable 7.2V

Chemical System: Nickel-Metal Hydride (NiMH)

**Designation:** ANSI-7.2H5 **Battery Voltage:** 7.2 Volts

Average Capacity: 150 mAh (to 6.0 volts)

(Based on 30 mA (0.2C) discharge rate)

Average Weight: 41.0 grams (1.5 oz.)

**Volume:** 21.7 cubic centimeters (1.3 cubic inch)

Jacket: Plastic

#### **Internal Resistance**

The internal resistance of the cell varies with state of charge, as follows:

Cell Charged
1000 milliohms
1500 milliohms
(tolerance of ±20% applies to above values)

### AC Impedance (No Load)

The impedance of the charged cell varies with frequency, as follows:

Frequency (Hz) Impedance (milliohms

(Charged Cell) 950

Note: Above values based on AC current set at 1.0 ampere. Value tolerances are ±20%

### **Operating and Storage Temperatures**

1000

Ranges of temperature applicable to operation of the NH22 cells are:

Charge @ 0.1C:  $32^{\circ}F$  to  $122^{\circ}F$  (0°C to  $50^{\circ}C$ ) Discharge @ 0.1C:  $-4^{\circ}F$  to  $122^{\circ}F$  ( $-20^{\circ}C$  to  $50^{\circ}C$ )

**Storage:** – 40°F to 122°F (-40°C to 50°C) ( 6 Months Max. )

- 4°F to 95°F (-20°C to 35°C)

( 2 Years Max. )

Operating at extreme temperature will significantly affect service and cycle life.

### **Important Notice**

This data sheet contains information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

Copyright © Eveready Battery Co. Inc. - All Rights Reserved

Form No. EBC - 7105D Page 1 of 1